

## Surface Burning Characteristics of Uniboard Products

Product Type	ASTM E84 (US)		CAN/ULC-S102		Class
	Flame Spread	Smoke Development	Flame Spread	Smoke Development	
5/8 raw particleboard	115	120	140	125	III or C
5/8 laminated particleboard	125	120	130	135	III or C
3/4 Nu Green raw particleboard	88-98				III or C
3/4 raw MDF	135	115	145	125	III or C
3/4 raw Ultra Lite MDF	75	115	80	115	III or C
3/4 laminated MDF	145	80	175	110	III or C

	Flame Spread	Smoke Development
Class I or A	0-25	max. 450
Class II or B	26-75	max. 450
Class III or C	76-200	max. 450