

Classic (Grade 130)

Technical Specifications

Properties	ANSI A208.2-2009 (Grade 130)	
	Metric	Imperial
Moisture content	Max. 9%	
Density range	700-745 kg/m ³	43.7-46.5 lb/ft ³
	Typical density value for Uniboard mills	
Thickness tolerance:		
Between panels	± 0.125 mm	± 0.005 in
Within panels	± 0.125 mm	± 0.005 in
Modulus of rupture	21.6 N/mm ²	3,130 psi
Modulus of elasticity	2,160 N/mm ²	313,000 psi
Internal bond	0.54 N/mm ²	78 psi
Linear expansion	< 0.33%	
Screw holding:		
Face	988 N	222 lb
Core	787 N	177 lb
Formaldehyde emission	0.11 ppm (CARB 2) > 8 mm	0.13 ppm (CARB2) ≤ 8 mm
Length-Width	± 2.0 mm	± 0.08 in

NU Green[®] 2 NAUF MDF Classic meets the requirements of ANSI A208.2-2009/Grade 130 and is available as FSC[®] certified
 NU Green[®] 2 NAUF MDF Classic meets CARB Phase 2 standards



www.uniboard.com

© Registered Trademark of Uniboard Canada Inc.



CARB
COMPLIANT

A Pfeleiderer AG company